

97.5/ 1.5 / 1

(97.5 Pb / 1.5 Ag / 1 Sn Lead-Silver-Sn Soft Solder)

NOMINAL COMPOSITION

Tin	.75%-1.25%	Antimony	0.4% Max	Arsenic	0.02% Max
Silver	1.3%-1.7%	Cadmium	0.001% Max	Iron	0.02% Max
Lead	Remainder	Copper	0.30% Max	Aluminum	0.005% Max
Zinc	0.005% Max	Bismuth	0.25% Max		

PHYSICAL PROPERTIES

Color	Silver White
Melting Point (Solidus)	588°F (309°C)
Flow Point (Liquidus)	588°F (309°C)
Specific Gravity	11.29
Density (Lbs/in ³)	0.408
Electrical Conductivity (% IACS)	N/A
Electrical Resistivity (Microhm-cm)	N/A

*IACS = International Annealed Copper Standard

SOLDERING CHARACTERISTICS

97.5/1.5/1 is a general purpose soft solder used in applications involving soldering of copper and copper alloys and/or ferrous base alloys. This alloy should not be used in soldering of potable water systems due to its high lead content. A lead free alloy should be used instead. For water potable systems LM recommends Silver/Copper/Tin system such as Silvabrite[®]-No Lead, or Tin/Silver systems such as Silvabrite and /or Silvabrite 6. The use of TEC flux is recommended in conjunction with this alloy.

PROPERTIES OF SOLDER JOINTS

The properties of a soldered joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Joint clearances of 0.003 - 0.005 in. (0.076 - 0.127 mm) per side are optimum for achieving highest joint strength. Joints with increased clearances can still produce adequate joint strengths depending on final operating conditions.

AVAILABLE FORMS

Wire, and strip.

SPECIFICATIONS

97.5/ 1.5/ 1 alloy conforms to the following specifications:

- American Society for Testing and Materials (ASTM) B32 Ag 1.5

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: A00000392, Legacy Code: 63-015.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for 97.5/1.5/1.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.